

# Daelim XP-9200

Metallocene Linear Low Density Polyethylene



Blown Film

## Characteristics

- Excellent Processability
- Excellent Dart Impact
- Excellent Sealability
- Very Low Extractables

## Applications

- General Film for High Strength
- Lamination Film
- Green House Film

## Processing Recommendation

- Stock Temp. : 160 ~ 190 °C

## Specification data

- Meets FDA Regulation 177. 1520

## Nominal Physical Properties

Properties	Test Method	Unit	Value
Density	ASTM D1505	g/cm <sup>3</sup>	0.918
Melt Index (190 °C, 2.16 kg)	ASTM D1238	g/10min	1.5
Additives	-	-	AO, AB, Slip, PPA
Melting Point	ASTM D3418	°C	116
Xylene Soluble	Daelim Method	wt%	0.7
Dart impact Strength	ASTM D1709	g	500
Haze	ASTM D 1003	%	7
Seal Initiation Temperature (HGT, 2.8KG, 0.5sec)	Daelim Method	°C	95

Remark> 1. Film processing condition : 180 °C, BUR 2.5, Film thickness 0.030mm

2. Additives : AO (Anti-Oxidant), AB (Anti-Blocking Agent), Slip (Slip Agent), PPA (Polymer Processing Aid)

3. Physical properties of film can be changed by machine type and processing condition



TEL : 82-2-3708-3341, FAX: 82-2-753-4958

**Distributed By Daelim Corporation**

TEL : 82-2-3708-3312, FAX : 82-2-771-8926