**a** +7 843 293 27 44 **a** +7 843 293 27 34 nolimerinc@mail.ru

## WWW.POLIETILENY.RU

## **BL6200**

# **High Density Polyethylene**

#### **Description**

BL6200- is a HDPE resin produced via Slurry process technology and suitable for use in blow moulding application. BL6200 is designed to offer high speed processability, good ESCR.

### **Application**

Bottle (small) and household product (shampoo, bleach, Cosmetics).

Properties			
Physical	<b>Testing methods</b>	Nominal values	
Density	ASTM D 1505	g/cm <sup>3</sup>	0.956-0.961
Melt Flow Rate	ASTM D 1238	g/10min	0.32-0.44
Mechanical			
Tensile Strength at Yield (min.)	ASTM D 638	kg/cm <sup>2</sup>	240
Elongation at Break (min.)	ASTM D 638	0/0	500
Flexural Modulus (min.)	ASTM D790	kg/cm <sup>2</sup>	11,000
Impact			
Izod Impact Strength (23 <sup>o</sup> C) (min.)	ASTM D256	kg cm/cm	10
Thermal			
Vicat Softening Point (min.)	ASTM D1525	°C	123
Additional properties			
Rockwell Hardness (min.)	ASTM D785	R	55
Environmental Stress Cracking Resistance (F50) (min.)	ASTM D1693	hr	100